



DIVERSIFIED
TESTING LABORATORIES, INC.
 WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

December 31, 2024

Ms. Laine Letourneau
 INTEGRA INTERNATIONAL, INC.
 4725 Northgate Blvd
 Unit A
 Myrtle Beach, SC 29577

Reference: Laboratory Test Report
 Lab Identification No. 62689
 Invoice No. 93991

Dear Ms. Letourneau:

One (1) fabric sample, identified as **DELTA**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	18.46
2	0.0	24.63
3	0.0	18.51
4	0.0	26.29
5	0.0	20.29
6	0.0	22.02
7	0.0	23.91
8	0.0	20.85
9	0.0	17.55
<u>10</u>	<u>0.0</u>	<u>22.07</u>
AVG	0.0	21.46

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

