



**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
 WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
 P.O. BOX 4004  
 BURLINGTON, NORTH CAROLINA 27215  
 PHONE (336) 227-7710 • FAX (336) 227-1175  
 www.diversifiedtestinglabs.com

December 3, 2024

Ms. Laine Letourneau  
 INTEGRA INTERNATIONAL, INC.  
 4725 Northgate Blvd  
 Unit A  
 Myrtle Beach, SC 29577

Reference: Laboratory Test Report  
 Lab Identification No. 62400  
 Invoice No. 93696

Dear Ms. Letourneau:

One (1) fabric sample, identified as **Thin Stripe**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". The results are as follows:

**Test Results**

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	2.26
2	0.0	7.53
3	0.0	6.34
4	0.0	3.50
5	0.0	8.89
6	0.0	9.63
7	0.0	9.23
8	0.0	10.99
9	0.0	10.07
<u>10</u>	<u>0.0</u>	<u>8.49</u>
<b>AVG</b>	<b>0.0</b>	<b>7.69</b>

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

